

# #8612 Miles Eco-Powder Strip RTU

## T E C H N I C A L   D A T A   S H E E T

---

*Description:* #8612 is formulated to dissolve cured coatings including: powder coating, and wet-applied cured coatings from aluminum, zinc, magnesium, brass, stainless steel and steel substrates. Used in conjunction with #8635 Evaporation Inhibitor at 5% concentration.

*Directions:* MILES#8612 is a unique formula that is used as received with no water dilution, at temperatures of 165F to 185F. Immerse rework parts in an immersion strip tank with a lid, ventilation and a mixer, for 30 to 60 minutes. May be used at Room Temperature for TGIC Powder Coating Removal overnight. Accelerate Powder Coating Removal with 5% adds of MILES #8605 as required to maintain pH between 11.7-12.7

*Warning:* May be harmful if swallowed. May cause skin and eye irritation. Eye protection and rubber gloves are recommended when handling this product.

*First Aid:* In case of eye or skin contact flush with large amounts of water for 15 minutes. If irritation persists, see physician. In case of ingestion, do not induce vomiting; drink large quantities of water to dilute product. Get medical attention at once.

*Hazard Class:* Non-regulated

<i>Properties:</i>	pH:	11.7 - 12.7	Health:	2
	Specific Gravity:	1.04 - 1.06	Flammability:	0
	Color:	Translucent	Reactivity:	0