

8626 Miles Lightning Steel-Strip

T E C H N I C A L D A T A S H E E T

Description: MILES #8626 is used to strip, recycle and recover rework powder coating, e-coating and other finishes from steel substrates for paint re-process. MILES #8626 is also used daily to strip and clean coating Hooks, Racks and Fixtures.

Directions: Charge process tank with #8626 at 50% concentration by volume, 40% water and 10% #8635 Evaporation Blanket. Operate at temperatures of 195F to 200F. Strip time is usually 10 to 20 minutes per 2-3 mils of cured coating on parts. We recommend stripping Coating Hooks daily to keep film thickness down and obtain fastest stripping time.

Warning: May be harmful if swallowed. May cause skin and eye irritation. Eye protection and rubber gloves are recommended when handling this product.

First Aid: In case of eye or skin contact flush with large amounts of water for 15 minutes. If irritation persists, see physician. In case of ingestion, do not induce vomiting; drink large quantities of water to dilute product. Get medical attention at once.

Hazard Class: CORROSIVE LIQUID (POTASSIUM HYDROXIDE), 8, UN1814, PGII

Properties:	pH:	13.0 - 14.0	Health:	3
	Specific Gravity:	1.20 - 1.24	Flammability:	0
	Color:	Violet	Reactivity:	0